220002349162

中国认可
国际互认
检测
TESTING
CNAS L0690

TEST REPORT

Report No.: WT2025B01A04399

Entrusted by: Kiloxy shanghai Co., LTD

Sample Name: POLI

Test Type: Entrustment test

China Testing & Certification International Group Co.,Ltd.

National Research Center of Testing Techniques for Building Materials

WT2025B01A04399

ctc 国检集团

Notice

1. **This test report is invalid without the seal or cross-page seal.**
2. **This test report is invalid without the signatures of the related persons.**
3. **This test report is invalid if erased, altered or copied partially.**
4. **Any doubt should inform us within 15 days after receiving the test report.**
5. **The entrustment test samples and relevant information are provided by entrusted body, the laboratory does not responsible for authenticity. The results shown in this report refer only to the samples tested.**
6. **This test report is printed on anti-counterfeiting paper. Copies made from original should have grid shadings. The numbers on the back of the data sheet are random and do not related with the report.**

国检集团

Laboratory Contact information:

Address: No.1 Guanzhuang Dongli, Chaoyang District, Beijing, 100024, P.R. China.

Web: www.ctc.ac.cn

Customer online service platform: http://www.ctc-online.cn

Telephone of service reception: 400-010-0010, +86-10-51167681

Email of service reception: ywjd@ctc.ac.cn

Telephone of genuine enquiries and complaints: 400-010-0010, +86-10-51167679

扫描全能王
3亿人都在用的扫描App

China Testing & Certification International Group Co.,Ltd.

National Research Center of Testing Techniques for Building Materials

Test Report

Report No.: WT2025B01A04399

Sample Name	POLI	**Test Type**	Entrustment test
Entrusted By	Kiloxy shanghai Co., LTD	**Brand**	Kiloxy
Manufacture	Shanghai Jiafeng Coating Tech. CO., LTD	**Test Type**	Meet the requirements of testing
Receiving Date	Jul. 14, 2025	**Quantity of Samples**	500g
Production Date/ Batch No.	——	**Model/Size**	——
Test Methods	The method for the test items are detailed in the data pages.	**Test Date**	Aug. 10-11, 2025
Judgment Standards	Particulate matter removal rate		
Test Result	* See data page for the detailed test results. * **Date of issue:** 2025-08-13 **(Seal)**		

Remarks: (Provided by the client) Spray 250g of the sample onto three 1m² base papers.

Approved by: 徐升平 **Checked by:** 李倩男 **Compiled by:** 焦俊英

Address: No.1 Guanzhuang Dongli ,Chaoyang District, Beijing, China
Tel: 00-86-10-51167681 **P.C.:** 100024

ctc 国检集团

扫描全能王 3亿人都在用的扫描App

Test Report

Report No.: WT2025B01A04399

No.	Test item	Test results	Test methods
1	Particulate matter removal rate / (%)	35.00	QB/T 2761-2024 Appendix B

(Blank below)

Remark:

1. Test location: Guanzhuang.
2. Test description:
   ① Purification chamber volume: 1m³.
   ② Sample size for painting: 250g.
   ③ Testing time: 1 hour.
   ④ Environmental conditions: temperature 23±3 °C, relative humidity 50±10%.

End of the report

Address: No.1 Guanzhuang Dongli ,Chaoyang District, Beijing, China
Tel: 00-86-10-51167681 P.C.: 100024

ctc 国检集团
扫描全能王 3亿人都在用的扫描App