

思沃®化学 **PUD-909F**

特性	阴离子型脂肪族聚酯型聚氨酯水分散体
外观	半透明
含固量 (%)	33±1
PH 值	7.5-9.0
粘度 (mPa · s)	≤100
乳液粒径 (nm)	≤100
最低成膜温度 (°C)	5
助溶剂含量 (%)	不含 NMP、NEP、DMAC 等违禁物质
断裂伸长率 (%)	380
拉伸强度 (Mpa)	23.8
100%弹性模量 (Mpa)	6.4
60 度角下光泽	89-90
表干时间 (min)	≤30
实干时间 (min)	≤60
机械稳定性	好
耐黄变性能	涂膜不黄变
贮存	常温下保存 6 个月
包装	1000Kg/塑桶 200Kg/塑桶 120Kg/塑桶

应用：高性价比产品。涂膜有较高硬度，高亮度。有良好的乙醇稀释性能。有优异的耐磨性能、抗粘性能的和耐水性能，主要应用于印刷光油、墙体涂料、钢结构和木器涂料，以及丙烯酸乳液的改性等。不含有机锡、甲醛、重金属等违禁物质。

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.