

思沃®化学

PUD-910F、912F

特性	阴离子型脂肪族聚酯型聚氨酯水分散体
外观	白色半透明液体
含固量(%)	33±1
PH 值	7.0-9.5
粘度(mPa·s)	≤200
乳液粒径(nm)	≤100
助溶剂	不含 NMP、NEP、DMAC 等违禁物质
最低成膜温度(℃)	50
邵氏硬度(A):	94-96
60 度角下光泽	91-92
表干时间(min)	≤30
实干时间(min)	≤60
机械稳定性	好
耐黄变性能	涂膜不黄变
贮存	常温下保存 6 个月
包装	1000Kg/塑桶 200Kg/塑桶 120Kg/塑桶

应用：阴离子型的高分子量聚氨酯水分散体。涂膜快干、高硬度、高光泽。有优异的耐磨性能、抗粘性能，主要应用于印刷光油、木器涂料，以及丙烯酸乳液的改性等。PUD-912F 与 PUD-910F 技术指标基本同，但比 PUD-910F 有更好的耐酒精擦拭性能和在金属等底材上更好的附着力。不含有机锡、甲醛、重金属等违禁物质。

使用时建议加入 3-5%的二丙二醇单甲醚。

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.