

思沃®化学 U-674

特性	脂肪族聚酯型聚氨酯乳液
外观	乳白色液体
含固量 (%)	48-50
PH 值	7.0-9.5
粘度 (mPa · s)	≤1000
乳液粒径 (nm)	≤200
最低成膜温度 (°C)	≥0
最低活化温度 (°C)	70-80
VOC:	不含 NMP, NEP, DMAC 等, 含微量丙酮
机械稳定性	好
耐黄变性能	涂膜不黄变
贮存	常温下保存 6 个月
包装	1000Kg/塑桶 200Kg/塑桶 120Kg/塑桶

应用：高分子量聚氨酯乳液，非结晶型，胶膜柔软，有良好的回弹性，在较高的温度下有热活化性能。它对大多数合成材料和天然材料均具有优异的粘接性能。与 U-654 和 U-658 相比，本品具有更好的柔韧性和附着力。适宜于织物和皮革等基材的粘结。加入 2-5% 的水分散型聚异氰酸酯固化剂（如本公司生产的 EC-600）可显著增强其耐高温粘接性能。

用于热活化粘接工艺时，建议使用 80-90°C 或更高的温度，以确保干燥的胶层被充分激活。具体应用所需的实际温度取决于所施加的压力、保压时间及被粘接基材。存放超过六个月的产品，需经检测合格后方可使用。

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication. Nothing herein is to be construed as a warranty, express or otherwise. In all cases, it is the responsibility of the users to determine the applicability of such information or suitability of any products for their own purposes. Statements or suggestions concerning possible use of our products are made without representation or warranty that any such is free of patent infringement and are not recommendations to infringe on any patent.