

## Application

The activator can clean, degrease parts and speed up the setting time of cyanoacrylate adhesives. Curing effect is obtained in 1 - 4 seconds depending from type of adhesive, gap between parts and surfaces composition.

## properties

Property	Value	Test Method
Chemical nature	Aliphatic amine in organic solvent	
Appearance	Colorless	
Viscosity	1-2 mPa.s	
Vapor pressure	50 mbar	
Drying time	20-30s	
Activation effect on surface	8hours	

## Handling and Storage

Apply Method	Wipe, dipping,
Storage Method:	Below 25°C, tightly closed
Shelf life	12months@original package

## Direction for use

1. The Activator is applied on one surface and let to dry for a few seconds.
2. Always seal the bottle of the Activator immediately after use.
3. Should be reapplied after eight hours.

## Package available

NA

## Other Information

The data just as a guide. We cannot assume responsibility for the results obtained by customer's different process and conditions which we cannot control. It is suggested to adopt such precautions as may be advisable for the protection of property and of persons against any hazards. We recommend that customer test it before repetitive use;